

Rolled and Molded Rod Products - Property Comparison

			RM130	RM500A	RM504	RM505	RM511A	RM310	RM310E	RM315	
			Glass Fabric				Cotton (Canvas)				
			Epoxy		Phenolic	Melamine	Epoxy	Phenolic		Phenolic - Graphite	
PHYSICAL PROPERTIES											
Specific Gravity (0.500" OD)		-	1.84	1.85	1.79	1.95	1.85	1.34	1.34	1.35	
Rockwell Hardness (0.500" OD)		M Scale	105	110	110	110	110	90	90	90	
Moisture Absorption (0.500" OD)	Condition D ₁ -24/23	%	0.03	0.08	0.04	0.70	0.08	0.90	0.90	0.82	
Flexural Strength (0.500" OD)	Condition A	Axial	psi	65,200	85,300	59,700	54,500	85,300	18,400	18,400	18,500
Tensile Strength (0.500" OD)	Condition A	Axial	psi	41,200	55,900	37,000	32,300	55,900	8,900	8,900	9,600
Compressive Strength (0.500" OD)	Condition A	Axial	psi	52,600	73,600	68,000	60,900	73,600	28,600	28,600	28,400
THERMAL PROPERTIES											
Maximum Operating Temperature ¹	Electrical / Mechanical	°C	120 / 130	170 / 220	140 / 170	120 / 140	170 / 180	115 / 125	115 / 125	115 / 125	
Flammability Rating U.L. 94	Condition A	Class	V-0	HB	HB	V-0	HB	HB	HB	HB	

NOTE a: A double dash (--) indicates that the value has not been determined or is not applicable to the product.

NOTE b: All testing per ASTM D348 unless otherwise noted.

¹ NEMA LI-6: This temperature is a recommendation only and is based upon experience in various applications. The maximum operating temperature is dependent upon the application and should be investigated prior to use.



Rolled and Molded Rod Products - Property Comparison

			RM320	RM320LE	RM326	RM329	RM629	RM630	
			Cotton (Fine Weave Linen)				Paper		
			Phenolic		Epoxy	Melamine	Phenolic		
PHYSICAL PROPERTIES									
Specific Gravity (0.500" OD)		-	1.35	1.35	1.35	1.39	1.40	1.40	
Rockwell Hardness (0.500" OD)		M Scale	80	80	100	89	100	100	
Moisture Absorption (0.500" OD)	Condition D ₁ -24/23	%	0.85	0.85	0.51	2.20	0.58	0.58	
Flexural Strength (0.500" OD)	Condition A	Axial	psi	20,100	20,100	22,000	18,000	20,800	20,800
Tensile Strength (0.500" OD)	Condition A	Axial	psi	9,400	9,400	15,000	9,200	15,300	15,300
Compressive Strength (0.500" OD)	Condition A	Axial	psi	29,000	29,000	29,900	28,500	27,900	27,900
THERMAL PROPERTIES									
Maximum Operating Temperature ¹	Electrical / Mechanical	°C	115 / 125	115 / 125	115 / 125	115 / 125	140 / 140	140 / 140	
Flammability Rating U.L. 94	Condition A	Class	HB	HB	HB	V-1	HB	HB	

NOTE a: A double dash (--) indicates that the value has not been determined or is not applicable to the product.

NOTE b: All testing per ASTM D348 unless otherwise noted.

¹ NEMA LI-6: This temperature is a recommendation only and is based upon experience in various applications. The maximum operating temperature is dependent upon the application and should be investigated prior to use.